

## **GEAGROUND BASE SRT**

<b>Chemical Nature:</b>	emulsion of waxes, synthetic linking agents and auxiliary agents.
<b>Active Substance:</b>	approx. 18%
<b>pH:</b>	approx. 8,5
<b>Ionic Charge:</b>	anionic
<b>Aspect:</b>	yellow liquid
<b>Utilization:</b>	thermo reactive pre-bottom, indicated for finishes that need high upgrade effect.

### **PROPERTIES**

---

GEAGROUND BASE SRT is a Thermo Reactive Pre-bottom based on closing additives, waxes, thermo reactive components, and synthetic linking agents, which provide high upgrade effect to the finishes on low classified leathers with open grooves, ticks, and grubs. GEAGROUND BASE SRT must be applied in thermo dot on full grain or scoured leathers, in the proportion of 800-900g of the product to 100-200g anionic pigment. After the application of GEAGROUND BASE SRT it is necessary to emboss the leathers (pore or relax) at 120°C/150 ATM/4s in order to be possible to obtain the best yield of upgrade of the product. Afterwards, it is recommended to mill the leathers and finish them in accordance with the desired article. GEAGROUND BASE SRT provides the leathers excellent upgrade, good coverage and medium rubbery touch. After the upgrading process, the leather can receive correction painting to ascertain the color, touch change or gloss.