

GEATOP D 60

Chemical Nature:	waterborne aliphatic polyurethane and polyacrylates
Active Substance:	approx. 19%
pH:	approx. 9,0
Ionic Charge:	anionic
Film Hardness:	medium
Film Transparency:	dull
Aspect:	white liquid
Utilization:	finish final top

PROPERTIES

GEATOP D 60 is a specially elaborated final top for applications demanding excellent results in physical tests. GEATOP D 60 forms a good dull film, of excellent flexibility and resistance to dry and wet abrasion. GEATOP D60 has its physical properties optimized whenever it is cross linked with auxiliary products like aziridine 100% (GEAFIX 7) in the proportion of 1-3% of resin weight, depending on the required resistances. GEATOP D 60 can be applied with spray gun or thermodot systems, providing excellent distribution and surface uniformness.

Due to its particular properties, GEATOP D 60 finds specific use in nappas of motorcycle type, upholstery, and automotive leathers (after market) and all types of leathers that require high values of physical-mechanical resistance.